

TABLE II Composition and surface area of the coiled carbon fibres

Sample	Impurity	Composition (wt %)					Surface area (BET, m <sup>2</sup> g <sup>-1</sup> )
		Ni	S	H	O	C	
Carbon	H <sub>2</sub> S	0.25	0.09	1.4	1.0	97.26	352
Coils	Thiophene	0.25	0.03	1.0	0.6	98.12	293
Carbon Powder	H <sub>2</sub> S	-	0.10	0.33	0.5	-	-

(-) Not measured.